



Technical Data Sheet

Material	DWF 200 (AIR DECK)		
Type of coating	PVC		
Finish	Matt		
Total Thickness	2.75 mm		
Total weight	2900 ±2% gsm	DIN EN ISO 2286-2	
Piles Height	200 mm		
Tensile strength	warp / weft	2135 / 2687 N/5cm	ISO 1421
Tearing strength	warp / weft	725 / 636 N/5cm	DIN 53363
Elongation	warp / weft	53 / 72 %	ISO 1421
Adhesion strength	face / back	155 / 156 N/5cm	ISO 2411
Cold resistance	- 30°C ~ 70°C		DIN EN 1876-1
Recommended Max. Pressure	20 PSI		

Add: SIJIA Industrial Park No.8 Qiuzhen Road, Caojing Town, Jinshan District, Shanghai, China (Zip code: 251507).

Tel : 021-67256098

Fax : 021-67256098

Email:info@sijiacn.com

Website : www.sijiacn.com

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products.

Applications suggested do not release the customer to test material for its intended application.